

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
25.41	N/A	N/A	N/A	N/A	1100
25.42	N/A	N/A	N/A	N/A	1099
25.43	N/A	N/A	N/A	N/A	1097
25.44	N/A	N/A	N/A	N/A	1096
25.45	N/A	N/A	N/A	N/A	1094
25.46	N/A	N/A	N/A	N/A	1093
25.47	N/A	N/A	N/A	N/A	1091
25.48	N/A	N/A	N/A	1100	1090
25.49	N/A	N/A	N/A	1099	1088
25.50	N/A	N/A	N/A	1098	1087
25.51	N/A	N/A	N/A	1097	1085
25.52	N/A	N/A	N/A	1096	1084
25.53	N/A	N/A	1100	1095	1082
25.54	N/A	N/A	1099	1094	1081
25.55	N/A	N/A	1099	1093	1079
25.56	N/A	N/A	1098	1092	1078
25.57	N/A	N/A	1097	1091	1076
25.58	N/A	N/A	1096	1090	1075
25.59	N/A	N/A	1096	1089	1074
25.60	N/A	1100	1095	1088	1072
25.61	N/A	1099	1094	1087	1071
25.62	N/A	1099	1093	1086	1069
25.63	N/A	1098	1093	1085	1068
25.64	N/A	1097	1092	1084	1066
25.65	N/A	1097	1091	1083	1065
25.66	N/A	1096	1091	1082	1063
25.67	1100	1096	1090	1081	1062
25.68	1100	1095	1089	1080	1060
25.69	1099	1094	1088	1079	1059
25.70	1099	1094	1088	1078	1057
25.71	1098	1093	1087	1077	1056
25.72	1098	1092	1086	1076	1054
25.73	1097	1092	1086	1074	1053
25.74	1097	1091	1085	1073	1051
25.75	1096	1091	1084	1072	1050
25.76	1096	1090	1083	1071	1050
25.77	1096	1089	1083	1070	1049
25.78	1095	1089	1082	1069	1049
25.79	1095	1088	1081	1068	1048
25.80	1094	1087	1080	1067	1048
25.81	1094	1087	1080	1066	1047
25.82	1093	1086	1079	1065	1047
25.83	1093	1085	1078	1064	1046
25.84	1092	1085	1078	1063	1046
25.85	1092	1084	1077	1062	1046
25.86	1092	1084	1076	1061	1045
25.87	1091	1083	1075	1060	1045
25.88	1091	1082	1075	1059	1044
25.89	1090	1082	1074	1058	1044
25.90	1090	1081	1073	1057	1043

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

10 Minutes 30 Minutes 60 Minutes 120 Minutes 240+ Minutes

Dimension

25.91	1089	1080	1072	1056	1043
25.92	1089	1080	1072	1055	1042
25.93	1088	1079	1071	1054	1042
25.94	1088	1078	1070	1053	1042
25.95	1088	1078	1070	1052	1041
25.96	1087	1077	1069	1051	1041
25.97	1087	1077	1068	1050	1040
25.98	1086	1076	1067	1050	1040
25.99	1086	1075	1067	1049	1039
26.00	1085	1075	1066	1049	1039
26.01	1085	1074	1065	1048	1038
26.02	1084	1073	1064	1048	1038
26.03	1084	1073	1064	1047	1038
26.04	1083	1072	1063	1047	1037
26.05	1083	1072	1062	1046	1037
26.06	1083	1071	1062	1046	1036
26.07	1082	1070	1061	1045	1036
26.08	1082	1070	1060	1045	1035
26.09	1081	1069	1059	1044	1035
26.10	1081	1068	1059	1044	1034
26.11	1080	1068	1058	1044	1034
26.12	1080	1067	1057	1043	1033
26.13	1079	1066	1057	1043	1033
26.14	1079	1066	1056	1042	1033
26.15	1079	1065	1055	1042	1032
26.16	1078	1065	1054	1041	1032
26.17	1078	1064	1054	1041	1031
26.18	1077	1063	1053	1040	1031
26.19	1077	1063	1052	1040	1030
26.20	1076	1062	1051	1039	1030
26.21	1076	1061	1051	1039	1029
26.22	1075	1061	1050	1038	1029
26.23	1075	1060	1050	1038	1029
26.24	1075	1059	1049	1037	1028
26.25	1074	1059	1049	1037	1028
26.26	1074	1058	1048	1037	1027
26.27	1073	1058	1048	1036	1027
26.28	1073	1057	1047	1036	1026
26.29	1072	1056	1047	1035	1026
26.30	1072	1056	1046	1035	1025
26.31	1071	1055	1046	1034	1025
26.32	1071	1054	1045	1034	1025
26.33	1071	1054	1045	1033	1024
26.34	1070	1053	1044	1033	1024
26.35	1070	1053	1044	1032	1023
26.36	1069	1052	1043	1032	1023
26.37	1069	1051	1043	1031	1022
26.38	1068	1051	1042	1031	1022
26.39	1068	1050	1042	1031	1021
26.40	1067	1049	1041	1030	1021

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
26.41	1067	1049	1041	1030	1021
26.42	1067	1048	1040	1029	1020
26.43	1066	1048	1040	1029	1020
26.44	1066	1047	1040	1028	1019
26.45	1065	1047	1039	1028	1019
26.46	1065	1046	1039	1027	1018
26.47	1064	1046	1038	1027	1018
26.48	1064	1045	1038	1026	1017
26.49	1063	1045	1037	1026	1017
26.50	1063	1044	1037	1025	1017
26.51	1063	1044	1036	1025	1016
26.52	1062	1043	1036	1025	1016
26.53	1062	1043	1035	1024	1015
26.54	1061	1042	1035	1024	1015
26.55	1061	1042	1034	1023	1014
26.56	1060	1041	1034	1023	1014
26.57	1060	1041	1033	1022	1013
26.58	1059	1040	1033	1022	1013
26.59	1059	1040	1032	1021	1013
26.60	1058	1039	1032	1021	1012
26.61	1058	1039	1031	1020	1012
26.62	1058	1038	1031	1020	1011
26.63	1057	1038	1030	1019	1011
26.64	1057	1037	1030	1019	1010
26.65	1056	1037	1030	1019	1010
26.66	1056	1036	1029	1018	1009
26.67	1055	1036	1029	1018	1009
26.68	1055	1035	1028	1017	1008
26.69	1054	1035	1028	1017	1008
26.70	1054	1034	1027	1016	1008
26.71	1054	1034	1027	1016	1007
26.72	1053	1033	1026	1015	1007
26.73	1053	1032	1026	1015	1006
26.74	1052	1032	1025	1014	1006
26.75	1052	1031	1025	1014	1005
26.76	1051	1031	1024	1013	1005
26.77	1051	1030	1024	1013	1004
26.78	1050	1030	1023	1012	1004
26.79	1050	1029	1023	1012	1004
26.80	1049	1029	1022	1012	1003
26.81	1049	1028	1022	1011	1003
26.82	1048	1028	1021	1011	1002
26.83	1047	1027	1021	1010	1002
26.84	1046	1027	1020	1010	1001
26.85	1046	1026	1020	1009	1001
26.86	1045	1026	1020	1009	1000
26.87	1044	1025	1019	1008	1000
26.88	1043	1025	1019	1008	999
26.89	1043	1024	1018	1007	998
26.90	1042	1024	1018	1007	997

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

10 Minutes 30 Minutes 60 Minutes 120 Minutes 240+ Minutes

Dimension

26.91	1041	1023	1017	1006	997
26.92	1040	1023	1017	1006	996
26.93	1040	1022	1016	1006	995
26.94	1039	1022	1016	1005	994
26.95	1038	1021	1015	1005	993
26.96	1037	1021	1015	1004	992
26.97	1037	1020	1014	1004	991
26.98	1036	1020	1014	1003	991
26.99	1035	1019	1013	1003	990
27.00	1035	1019	1013	1002	989
27.01	1034	1018	1012	1002	988
27.02	1033	1018	1012	1001	987
27.03	1032	1017	1011	1001	986
27.04	1032	1016	1011	1000	985
27.05	1031	1016	1010	1000	984
27.06	1030	1015	1010	999	984
27.07	1029	1015	1010	998	983
27.08	1029	1014	1009	997	982
27.09	1028	1014	1009	996	981
27.10	1027	1013	1008	994	980
27.11	1026	1013	1008	993	979
27.12	1026	1012	1007	992	978
27.13	1025	1012	1007	991	978
27.14	1024	1011	1006	990	977
27.15	1024	1011	1006	989	976
27.16	1023	1010	1005	988	975
27.17	1022	1010	1005	987	974
27.18	1021	1009	1004	986	973
27.19	1021	1009	1004	984	972
27.20	1020	1008	1003	983	972
27.21	1019	1008	1003	982	971
27.22	1018	1007	1002	981	970
27.23	1018	1007	1002	980	969
27.24	1017	1006	1001	979	968
27.25	1016	1006	1001	978	967
27.26	1015	1005	1000	977	966
27.27	1015	1005	1000	976	966
27.28	1014	1004	998	974	965
27.29	1013	1004	996	973	964
27.30	1012	1003	994	972	963
27.31	1012	1003	992	971	962
27.32	1011	1002	990	970	961
27.33	1010	1002	988	969	960
27.34	1010	1001	987	968	959
27.35	1009	1001	985	967	959
27.36	1008	1000	983	966	958
27.37	1007	998	981	964	957
27.38	1007	995	979	963	956
27.39	1006	993	977	962	955
27.40	1005	991	975	961	954

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

10 Minutes 30 Minutes 60 Minutes 120 Minutes 240+ Minutes

Dimension

27.41	1004	989	973	960	953
27.42	1004	986	971	959	953
27.43	1003	984	969	958	952
27.44	1002	982	967	957	951
27.45	1001	980	965	956	950
27.46	1001	977	963	954	948
27.47	1000	975	962	953	946
27.48	997	973	960	952	943
27.49	993	970	958	951	941
27.50	990	968	956	950	939
27.51	987	966	954	947	937
27.52	983	964	952	945	934
27.53	980	961	950	942	932
27.54	977	959	948	939	930
27.55	973	957	945	937	928
27.56	970	955	943	934	926
27.57	967	952	940	931	923
27.58	963	950	938	929	921
27.59	960	948	935	926	919
27.60	957	946	933	923	917
27.61	953	943	930	921	914
27.62	950	941	928	918	912
27.63	948	939	925	915	910
27.64	947	937	923	913	909
27.65	945	934	920	910	908
27.66	943	932	918	909	907
27.67	942	930	915	908	906
27.68	940	928	913	907	905
27.69	938	926	910	906	904
27.70	937	923	909	904	902
27.71	935	921	908	903	901
27.72	933	919	907	902	900
27.73	932	917	906	901	899
27.74	930	914	905	900	898
27.75	928	912	904	899	897
27.76	927	910	903	898	896
27.77	925	909	902	897	895
27.78	923	908	901	896	894
27.79	922	908	900	894	893
27.80	920	907	900	893	892
27.81	918	906	899	892	891
27.82	917	905	898	891	889
27.83	915	904	897	890	888
27.84	913	903	896	889	887
27.85	912	903	895	888	886
27.86	910	902	894	887	885
27.87	909	901	893	886	884
27.88	909	900	892	886	883
27.89	908	899	891	885	882
27.90	907	898	890	884	881

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

10 Minutes 30 Minutes 60 Minutes 120 Minutes 240+ Minutes

Dimension

27.91	906	898	889	883	880
27.92	906	897	888	882	879
27.93	905	896	887	881	878
27.94	904	895	886	880	876
27.95	904	894	885	879	875
27.96	903	893	884	878	874
27.97	902	893	883	878	873
27.98	901	892	883	877	872
27.99	901	891	882	876	871
28.00	900	890	881	875	870
28.01	899	889	880	874	869
28.02	899	888	879	873	868
28.03	898	887	878	872	867
28.04	897	886	877	871	866
28.05	896	885	876	870	865
28.06	896	884	875	870	865
28.07	895	882	874	869	864
28.08	894	881	873	868	863
28.09	894	880	872	867	862
28.10	893	879	871	866	861
28.11	892	878	870	865	860
28.12	891	877	870	864	859
28.13	891	876	869	863	858
28.14	890	875	868	862	857
28.15	889	874	867	862	856
28.16	887	873	866	861	855
28.17	886	872	865	860	855
28.18	884	871	864	859	854
28.19	883	869	863	858	853
28.20	881	868	862	857	852
28.21	880	867	861	856	851
28.22	878	866	860	855	850
28.23	877	865	859	854	N/A
28.24	875	864	858	854	N/A
28.25	874	863	857	853	N/A
28.26	872	862	857	852	N/A
28.27	871	861	856	851	N/A
28.28	869	860	855	850	N/A
28.29	868	859	854	N/A	N/A
28.30	866	858	853	N/A	N/A
28.31	865	856	852	N/A	N/A
28.32	863	855	851	N/A	N/A
28.33	862	854	850	N/A	N/A
28.34	860	853	N/A	N/A	N/A
28.35	859	852	N/A	N/A	N/A
28.36	857	851	N/A	N/A	N/A
28.37	856	850	N/A	N/A	N/A
28.38	854	N/A	N/A	N/A	N/A
28.39	853	N/A	N/A	N/A	N/A
28.40	851	N/A	N/A	N/A	N/A

TempTab 300

Batch SMK

(850-1100 C)

===== Sintering Schedule =====

10 Minutes 30 Minutes 60 Minutes 120 Minutes 240+ Minutes

Dimension

28.41

850

N/A

N/A

N/A

N/A