

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
25.41	N/A	N/A	N/A	N/A	2012
25.42	N/A	N/A	N/A	N/A	2010
25.43	N/A	N/A	N/A	N/A	2007
25.44	N/A	N/A	N/A	N/A	2005
25.45	N/A	N/A	N/A	N/A	2001
25.46	N/A	N/A	N/A	N/A	1999
25.47	N/A	N/A	N/A	N/A	1996
25.48	N/A	N/A	N/A	2012	1994
25.49	N/A	N/A	N/A	2010	1990
25.50	N/A	N/A	N/A	2008	1989
25.51	N/A	N/A	N/A	2007	1985
25.52	N/A	N/A	N/A	2005	1983
25.53	N/A	N/A	2012	2003	1980
25.54	N/A	N/A	2010	2001	1978
25.55	N/A	N/A	2010	1999	1974
25.56	N/A	N/A	2008	1998	1972
25.57	N/A	N/A	2007	1996	1969
25.58	N/A	N/A	2005	1994	1967
25.59	N/A	N/A	2005	1992	1965
25.60	N/A	2012	2003	1990	1962
25.61	N/A	2010	2001	1989	1960
25.62	N/A	2010	1999	1987	1956
25.63	N/A	2008	1999	1985	1954
25.64	N/A	2007	1998	1983	1951
25.65	N/A	2007	1996	1981	1949
25.66	N/A	2005	1996	1980	1945
25.67	2012	2005	1994	1978	1944
25.68	2012	2003	1992	1976	1940
25.69	2010	2001	1990	1974	1938
25.70	2010	2001	1990	1972	1935
25.71	2008	1999	1989	1971	1933
25.72	2008	1998	1987	1969	1929
25.73	2007	1998	1987	1965	1927
25.74	2007	1996	1985	1963	1924
25.75	2005	1996	1983	1962	1922
25.76	2005	1994	1981	1960	1922
25.77	2005	1992	1981	1958	1920
25.78	2003	1992	1980	1956	1920
25.79	2003	1990	1978	1954	1918
25.80	2001	1989	1976	1953	1918
25.81	2001	1989	1976	1951	1917
25.82	1999	1987	1974	1949	1917
25.83	1999	1985	1972	1947	1915
25.84	1998	1985	1972	1945	1915
25.85	1998	1983	1971	1944	1915
25.86	1998	1983	1969	1942	1913
25.87	1996	1981	1967	1940	1913
25.88	1996	1980	1967	1938	1911
25.89	1994	1980	1965	1936	1911
25.90	1994	1978	1963	1935	1909

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
25.91	1992	1976	1962	1933	1909
25.92	1992	1976	1962	1931	1908
25.93	1990	1974	1960	1929	1908
25.94	1990	1972	1958	1927	1908
25.95	1990	1972	1958	1926	1906
25.96	1989	1971	1956	1924	1906
25.97	1989	1971	1954	1922	1904
25.98	1987	1969	1953	1922	1904
25.99	1987	1967	1953	1920	1902
26.00	1985	1967	1951	1920	1902
26.01	1985	1965	1949	1918	1900
26.02	1983	1963	1947	1918	1900
26.03	1983	1963	1947	1917	1900
26.04	1981	1962	1945	1917	1899
26.05	1981	1962	1944	1915	1899
26.06	1981	1960	1944	1915	1897
26.07	1980	1958	1942	1913	1897
26.08	1980	1958	1940	1913	1895
26.09	1978	1956	1938	1911	1895
26.10	1978	1954	1938	1911	1893
26.11	1976	1954	1936	1911	1893
26.12	1976	1953	1935	1909	1891
26.13	1974	1951	1935	1909	1891
26.14	1974	1951	1933	1908	1891
26.15	1974	1949	1931	1908	1890
26.16	1972	1949	1929	1906	1890
26.17	1972	1947	1929	1906	1888
26.18	1971	1945	1927	1904	1888
26.19	1971	1945	1926	1904	1886
26.20	1969	1944	1924	1902	1886
26.21	1969	1942	1924	1902	1884
26.22	1967	1942	1922	1900	1884
26.23	1967	1940	1922	1900	1884
26.24	1967	1938	1920	1899	1882
26.25	1965	1938	1920	1899	1882
26.26	1965	1936	1918	1899	1881
26.27	1963	1936	1918	1897	1881
26.28	1963	1935	1917	1897	1879
26.29	1962	1933	1917	1895	1879
26.30	1962	1933	1915	1895	1877
26.31	1960	1931	1915	1893	1877
26.32	1960	1929	1913	1893	1877
26.33	1960	1929	1913	1891	1875
26.34	1958	1927	1911	1891	1875
26.35	1958	1927	1911	1890	1873
26.36	1956	1926	1909	1890	1873
26.37	1956	1924	1909	1888	1872
26.38	1954	1924	1908	1888	1872
26.39	1954	1922	1908	1888	1870
26.40	1953	1920	1906	1886	1870

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
26.41	1953	1920	1906	1886	1870
26.42	1953	1918	1904	1884	1868
26.43	1951	1918	1904	1884	1868
26.44	1951	1917	1904	1882	1866
26.45	1949	1917	1902	1882	1866
26.46	1949	1915	1902	1881	1864
26.47	1947	1915	1900	1881	1864
26.48	1947	1913	1900	1879	1863
26.49	1945	1913	1899	1879	1863
26.50	1945	1911	1899	1877	1863
26.51	1945	1911	1897	1877	1861
26.52	1944	1909	1897	1877	1861
26.53	1944	1909	1895	1875	1859
26.54	1942	1908	1895	1875	1859
26.55	1942	1908	1893	1873	1857
26.56	1940	1906	1893	1873	1857
26.57	1940	1906	1891	1872	1855
26.58	1938	1904	1891	1872	1855
26.59	1938	1904	1890	1870	1855
26.60	1936	1902	1890	1870	1854
26.61	1936	1902	1888	1868	1854
26.62	1936	1900	1888	1868	1852
26.63	1935	1900	1886	1866	1852
26.64	1935	1899	1886	1866	1850
26.65	1933	1899	1886	1866	1850
26.66	1933	1897	1884	1864	1848
26.67	1931	1897	1884	1864	1848
26.68	1931	1895	1882	1863	1846
26.69	1929	1895	1882	1863	1846
26.70	1929	1893	1881	1861	1846
26.71	1929	1893	1881	1861	1845
26.72	1927	1891	1879	1859	1845
26.73	1927	1890	1879	1859	1843
26.74	1926	1890	1877	1857	1843
26.75	1926	1888	1877	1857	1841
26.76	1924	1888	1875	1855	1841
26.77	1924	1886	1875	1855	1839
26.78	1922	1886	1873	1854	1839
26.79	1922	1884	1873	1854	1839
26.80	1920	1884	1872	1854	1837
26.81	1920	1882	1872	1852	1837
26.82	1918	1882	1870	1852	1836
26.83	1917	1881	1870	1850	1836
26.84	1915	1881	1868	1850	1834
26.85	1915	1879	1868	1848	1834
26.86	1913	1879	1868	1848	1832
26.87	1911	1877	1866	1846	1832
26.88	1909	1877	1866	1846	1830
26.89	1909	1875	1864	1845	1828
26.90	1908	1875	1864	1845	1827

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
26.91	1906	1873	1863	1843	1827
26.92	1904	1873	1863	1843	1825
26.93	1904	1872	1861	1843	1823
26.94	1902	1872	1861	1841	1821
26.95	1900	1870	1859	1841	1819
26.96	1899	1870	1859	1839	1818
26.97	1899	1868	1857	1839	1816
26.98	1897	1868	1857	1837	1816
26.99	1895	1866	1855	1837	1814
27.00	1895	1866	1855	1836	1812
27.01	1893	1864	1854	1836	1810
27.02	1891	1864	1854	1834	1809
27.03	1890	1863	1852	1834	1807
27.04	1890	1861	1852	1832	1805
27.05	1888	1861	1850	1832	1803
27.06	1886	1859	1850	1830	1803
27.07	1884	1859	1850	1828	1801
27.08	1884	1857	1848	1827	1800
27.09	1882	1857	1848	1825	1798
27.10	1881	1855	1846	1821	1796
27.11	1879	1855	1846	1819	1794
27.12	1879	1854	1845	1818	1792
27.13	1877	1854	1845	1816	1792
27.14	1875	1852	1843	1814	1791
27.15	1875	1852	1843	1812	1789
27.16	1873	1850	1841	1810	1787
27.17	1872	1850	1841	1809	1785
27.18	1870	1848	1839	1807	1783
27.19	1870	1848	1839	1803	1782
27.20	1868	1846	1837	1801	1782
27.21	1866	1846	1837	1800	1780
27.22	1864	1845	1836	1798	1778
27.23	1864	1845	1836	1796	1776
27.24	1863	1843	1834	1794	1774
27.25	1861	1843	1834	1792	1773
27.26	1859	1841	1832	1791	1771
27.27	1859	1841	1832	1789	1771
27.28	1857	1839	1828	1785	1769
27.29	1855	1839	1825	1783	1767
27.30	1854	1837	1821	1782	1765
27.31	1854	1837	1818	1780	1764
27.32	1852	1836	1814	1778	1762
27.33	1850	1836	1810	1776	1760
27.34	1850	1834	1809	1774	1758
27.35	1848	1834	1805	1773	1758
27.36	1846	1832	1801	1771	1756
27.37	1845	1828	1798	1767	1755
27.38	1845	1823	1794	1765	1753
27.39	1843	1819	1791	1764	1751
27.40	1841	1816	1787	1762	1749

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
27.41	1839	1812	1783	1760	1747
27.42	1839	1807	1780	1758	1747
27.43	1837	1803	1776	1756	1746
27.44	1836	1800	1773	1755	1744
27.45	1834	1796	1769	1753	1742
27.46	1834	1791	1765	1749	1738
27.47	1832	1787	1764	1747	1735
27.48	1827	1783	1760	1746	1729
27.49	1819	1778	1756	1744	1726
27.50	1814	1774	1753	1742	1722
27.51	1809	1771	1749	1737	1719
27.52	1801	1767	1746	1733	1713
27.53	1796	1762	1742	1728	1710
27.54	1791	1758	1738	1722	1706
27.55	1783	1755	1733	1719	1702
27.56	1778	1751	1729	1713	1699
27.57	1773	1746	1724	1708	1693
27.58	1765	1742	1720	1704	1690
27.59	1760	1738	1715	1699	1686
27.60	1755	1735	1711	1693	1683
27.61	1747	1729	1706	1690	1677
27.62	1742	1726	1702	1684	1674
27.63	1738	1722	1697	1679	1670
27.64	1737	1719	1693	1675	1668
27.65	1733	1713	1688	1670	1666
27.66	1729	1710	1684	1668	1665
27.67	1728	1706	1679	1666	1663
27.68	1724	1702	1675	1665	1661
27.69	1720	1699	1670	1663	1659
27.70	1719	1693	1668	1659	1656
27.71	1715	1690	1666	1657	1654
27.72	1711	1686	1665	1656	1652
27.73	1710	1683	1663	1654	1650
27.74	1706	1677	1661	1652	1648
27.75	1702	1674	1659	1650	1647
27.76	1701	1670	1657	1648	1645
27.77	1697	1668	1656	1647	1643
27.78	1693	1666	1654	1645	1641
27.79	1692	1666	1652	1641	1639
27.80	1688	1665	1652	1639	1638
27.81	1684	1663	1650	1638	1636
27.82	1683	1661	1648	1636	1632
27.83	1679	1659	1647	1634	1630
27.84	1675	1657	1645	1632	1629
27.85	1674	1657	1643	1630	1627
27.86	1670	1656	1641	1629	1625
27.87	1668	1654	1639	1627	1623
27.88	1668	1652	1638	1627	1621
27.89	1666	1650	1636	1625	1620
27.90	1665	1648	1634	1623	1618

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

Dimension	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
27.91	1663	1648	1632	1621	1616
27.92	1663	1647	1630	1620	1614
27.93	1661	1645	1629	1618	1612
27.94	1659	1643	1627	1616	1609
27.95	1659	1641	1625	1614	1607
27.96	1657	1639	1623	1612	1605
27.97	1656	1639	1621	1612	1603
27.98	1654	1638	1621	1611	1602
27.99	1654	1636	1620	1609	1600
28.00	1652	1634	1618	1607	1598
28.01	1650	1632	1616	1605	1596
28.02	1650	1630	1614	1603	1594
28.03	1648	1629	1612	1602	1593
28.04	1647	1627	1611	1600	1591
28.05	1645	1625	1609	1598	1589
28.06	1645	1623	1607	1598	1589
28.07	1643	1620	1605	1596	1587
28.08	1641	1618	1603	1594	1585
28.09	1641	1616	1602	1593	1584
28.10	1639	1614	1600	1591	1582
28.11	1638	1612	1598	1589	1580
28.12	1636	1611	1598	1587	1578
28.13	1636	1609	1596	1585	1576
28.14	1634	1607	1594	1584	1575
28.15	1632	1605	1593	1584	1573
28.16	1629	1603	1591	1582	1571
28.17	1627	1602	1589	1580	1571
28.18	1623	1600	1587	1578	1569
28.19	1621	1596	1585	1576	1567
28.20	1618	1594	1584	1575	1566
28.21	1616	1593	1582	1573	1564
28.22	1612	1591	1580	1571	1562
28.23	1611	1589	1578	1569	N/A
28.24	1607	1587	1576	1569	N/A
28.25	1605	1585	1575	1567	N/A
28.26	1602	1584	1575	1566	N/A
28.27	1600	1582	1573	1564	N/A
28.28	1596	1580	1571	1562	N/A
28.29	1594	1578	1569	N/A	N/A
28.30	1591	1576	1567	N/A	N/A
28.31	1589	1573	1566	N/A	N/A
28.32	1585	1571	1564	N/A	N/A
28.33	1584	1569	1562	N/A	N/A
28.34	1580	1567	N/A	N/A	N/A
28.35	1578	1566	N/A	N/A	N/A
28.36	1575	1564	N/A	N/A	N/A
28.37	1573	1562	N/A	N/A	N/A
28.38	1569	N/A	N/A	N/A	N/A
28.39	1567	N/A	N/A	N/A	N/A
28.40	1564	N/A	N/A	N/A	N/A

TempTab 300

Batch SMK

(1562-2012 F) ===== Sintering Schedule =====

	10 Minutes	30 Minutes	60 Minutes	120 Minutes	240+ Minutes
Dimension	28.41	1562	N/A	N/A	N/A